



CORPORATE HEAD OFFICE  
Specialty Polymer Coatings  
#101, 20529 - 62nd Avenue, Langley, BC, CANADA V3A 8R4  
Tel: (604) 514-9711 • Fax: (604) 514-9722

U.S.A. HEAD OFFICE  
Specialty Polymer Coatings USA, Inc  
22503 FM521, Angleton, Texas, 77515, USA  
Tel: (281) 595-3530 • Fax: (281) 595-3717

---

## PRODUCT DATA SHEET

## SP-9888<sup>®</sup> GROUT AND SEALING COMPOUND

---

**DESCRIPTION:** Specialty Polymer Coatings, Inc.'s SP-9888<sup>®</sup> Grout and Sealing Compound is a solvent-free, no VOCs, 100% solids two-component epoxy / amine cured polymer. It is used for grouting and sealing purposes for various pipeline and tank floor applications.

**ADVANTAGES:**

- 100% Solids - No VOCs.
- Solvent free.
- Provides excellent grouting and sealing for mating steel surfaces.

**USES:**

- Grouting of pipe prior to installation of repair / reinforcing sleeves or clamps.
- Sealing compound for application under repair / reinforcing sleeves or clamps, hot tap fittings, and split sleeve (clam) fittings.
- Grouting and sealing compound for use on tank floors.

**APPLICATION:** Brush or Roller or Gloved Hand

**SURFACE PREPARATION:** As per client's specification.

**FILM THICKNESS:** May be applied up to thickness of 13 mm (0.50 inch).

**MIXING RATIO:** By Volume: 2 Parts Base to 1 Part Hardener

**RE-COAT INTERVAL:**

- Minimum: 3 Hours @ 25°C (77°F)
- Maximum: 24 Hours @ 25°C (77°F)
- Re-Coat SP-9888<sup>®</sup> Grout and Sealing Compound with SP-9888<sup>®</sup> Spray Grade.
- Re-Coat Interval may vary depending upon the substrate temperature.

All information, recommendations, and test performance results herein were obtained in a controlled environment and SPC makes no claim that the data and tests accurately represent all environments and specific project specification requirements. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating. SPC products are sold with the understanding that the purchaser or user is solely responsible for determining their suitability for any purpose, and that the purchaser or user assumes all risks and liability associated with the use of the product. No guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. The information herein is not to be copied, used in evidence, released for publication, or public distribution without written permission from Specialty Polymer Coatings.



---

## PRODUCT DATA SHEET

## SP-9888<sup>®</sup> GROUT AND SEALING COMPOUND

---

### HANDLING PROPERTIES:

Pot Life: 30-40 Minutes @ 25°C (77°F)

Dry Time (ASTM D1640):

Touch Dry Time: 1 Hour 30 Minutes @ 25°C (77°F)

Dry Hard Time: 3 Hours 30 Minutes @ 25°C (77°F)

Substrate Temperature: The substrate temperature should be above 10°C (50°F). The substrate temperature must be a minimum of 3°C (5°F) above the dew point temperature before proceeding with the grouting or sealing application to avoid condensation.

Storage / Shelf Life: Store in a cool, dry, well-ventilated area at temperatures between 5°C (41°F) and 40°C (104°F). Keep the container lids sealed when not in use. The Shelf Life is a maximum of 24 months from the Date of Manufacture if the material is in unopened containers.

### LIQUID PROPERTIES:

	<u>BASE</u>	<u>HARDENER</u>	<u>MIXED</u>
Appearance .....	Tan	Beige	Tan
Volume Solids Content (%) .....	100	100	
Specific Gravity (ASTM D1475) .....	1.47	1.64	
Specific Gravity (ASTM D1475) .....	Base & Hardener Mixed: 1.52		

**SAFETY:** Read the Material Safety Data Sheets before use.

**EFFECTIVE DATE:** October 24, 2016